



LOGICROOF V-GR

Glass fiber reinforced PVC membrane for single-ply waterproofing of ballasted and inverted flat roofs

Product description

LOGICROOF V-GR is a glass fiber reinforced PVC membrane, which is used for single-ply waterproofing of ballasted and inverted non-exposed flat roofs. The multi-layer material is produced by co-extrusion on a base of premium quality plasticized polyvinyl chloride (PVC-P).



Glass fiber reinforcement provides an increased resistance to punctures and mechanical impacts of sharp objects.

Performance of works

The waterproofing PVC membrane is loose laid. Overlap seams are welded by hot air welding equipment, such as manual hot air welding machines and pressure rollers or automatic hot air welding machines with temperature control. Contact with all materials containing bitumen or solvents should be avoided. Direct contact with polymeric materials made of polystyrene (EPS, XPS) is not allowed.

Storage

Rolls of synthetic membranes are delivered on pallets. Every roll is packed in the additional individual pack. Rolls should be stored lying down on pallets fully protected from moisture with clean canvas tarpaulins. Keep the minimum distance of 1 m from any source of heat. Shelf life if all storage requirements are met: 18 months from the date of production.

Main characteristics

Properties	Performance	Test method
Thickness, mm	1.5, 2.0, 2.4 (-5/+10%)	EN 1849-2
Mass per unit area, kg/m ²	1.8, 2.5, 3.2	EN 1849-2
Length x width, m	20 x 2.05, 15 x 2.05, 15 x 2.05	EN 1848-2
Tensile strength L / T, N/50 mm	≥800 / ≥600	EN 12311-2
Elongation, %	≥200	EN 12311-2
Tear resistance, N	≥150	EN 12310-2
Resistance to static load, kg	≥20	EN 12730 B
Resistance to impact on rigid / soft base, mm	≥800 / ≥1000 (1.5 mm) ≥1400 / ≥1800 (2.0 mm) ≥1500 / ≥1900 (2.4 mm)	EN 12691
Peel resistance of joints, N/50 mm	≥300	EN 12316-2
Shear resistance of joints, N/50 mm	≥700	EN 12317-2
Foldability at low temperature, °C	≤-25	EN 495-5
Watertightness during 24 h at a pressure of 10 kPa	Pass	EN 1928-2 B